



PT Basis Pancakarya

Jl. Raya Sumber Jaya No. 61, Tambun 17510, Bekasi Timur, Jawa Barat, Indonesia
Telp : 021- 9300-9536 Fax : 021 8242-8098 Email : cs@Basisrubber.com

TECHNICAL DATA SPECIFICATION

Rubber Compound NR-SP75

General Information

Colour	: Black
Cas Number	: N/A
Density	: 1, 20 g/cm ³
Base Elastomers	: NR + BR

Product Description

Rubber Compound NR-S75 is a black-fast curing- rubber compound for used in footwear industri.

Cure Properties

T5	: 1,5 mins
Cure at 150°C	: 4,0 mins

Physicals Properties

IRHD	: 75
Tensile strength	: 21 Mpa
Elongation at Break	: 300 %

Guaranteed Storage Time : 5 Days if store in cool room. Avoid direct sunlight.